

LONGLITE**酚醛樹脂成型材料****CCP**

UL File: E59481
 Form : Granular
 Storage Life : 1 Year

Phenolic Molding Compound

PMC – T33J

301 SONGKIANG ROAD,
 7TH FL. TAIPEI, TAIWAN
 TEL: (02)25038131
 FAX: (02)25033378

技術資料(Technical Information)**品質特性表(properties)**

測試項目 (Test Items)		測試方法 (Test method)	代表值 (typical value)	
品 級(Grade)		JIS	T33J	Unit
一般特性 (Physical properties)	比重 Specific Gravity	K7112	1.37	---
	吸水率 Water Absorption(N)	K6911	0.40	%
	收縮率 Molding Shrinkage	K6915	1.30	%
機械特性 (Mechanical properties)	夏式衝擊強度 Charpy Impact	K7111	3.3	Kgf/cm
	曲折強度 Flexural Strength	K7203	9.0	kgf/mm ²
	引張強度 Tensile Strength	K6911	56	Mpa
	熱變形溫度 Temp. of deflection	K7207	160	°C
電氣特性 (Electrical properties)	耐電壓 Dielectric Strength	K6915	9	KV/mm
	常態絕緣 Insulation Res.(N)	K6915	10 ¹⁰	Ohm
	煮沸絕緣 Insulation Res.(B)	K6915	10 ⁸	Ohm
UL 相關	UL 94 耐燃		6.0	mm/V-0
	CTI 耐電蝕		4	---
	耐電弧		7	---
	相對熱指數		150	°C

上述特性值為典型值非保證值。

The above values of properties are typical value , not guaranteed.

產 品 描 述 (Product description)

酚醛成型材料，無機/有機材填充，耐熱性佳，機械強度佳。

Phenolic moulding compound, inorganically filled, organically filled, good heat resistant, good mechanical properties.

用 途 (Application area)

廚房部品、電氣部品。

Houseware appliance part、electrical application

批 號 定 義 (Lot No.)



建 議 成 形 條 件 (Recommended Moulding Condition)

壓縮/移送成型 (compression/trasfor)

模溫 Mould temperature	150-180℃
硬化時間 Curing time(sec/mm)	25 - 35
模腔壓力 Cavity molding pressure	>20MPA
預熱料溫 Temperature of heating	80 - 100℃

射出成型 (Injection)

料管溫度(Barrel Temp.)	80 ± 10 °C
模具溫度(Mold Temp.)	175 ± 15 °C
背壓(Back Pressure)	Under 10 kgf/cm ²

保 存 條 件 Storage Condition

儲存溫度 Storage Temperature	25 ± 10 °C
儲存濕度 Storage Humidity	40 - 60 % RH
儲存時間 Storage Life	12 months

包 裝 Packaging

紙袋包裝 25kg (25 kg/ paper bag)